

10/552940

JC20 Rec'd PCT/PTO 14 OCT 2003

OFGS File No: P/3240-105

English Translation of claims to
International Preliminary Examination
Report PCT/EP2004/003162 filed 25
March 2004.

What is claimed is

JC20 Rec'd PCT/PTO 1 4 OCT 2005

1. A molded body obtained via a shaping process that takes place under pressure, composed of

5

- at least one plant- or animal-derived fiber material,
- at least one thermoplastic or thermoset from the group of polyethylene, polypropylene, PVC, melamine, polyurethane, polyester, polyamide, polymethyl meth-
- 10 acrylate, polyvinyl acetate, polystyrene, poly-carbonate, polybutene, and
- at least one water-binding biopolymer,

and also, based on the total weight, if appropriate
15 from 0.2 to 20% by weight of plasticizers, fillers, adhesion promoters, lubricants, heat stabilizers and/or UV stabilizers, antioxidants, or flame retardants,

characterized in that

20

its water content immediately after its production is > 8.0% by weight, preferably $\geq 8.5\%$ by weight, particularly preferably $\geq 9.0\%$ by weight, and in that it is not expanded.

25

2. The molded body as claimed in claim 1, **characterized in that** its water content is up to 15% by weight, preferably up to 12% by weight.

30

3. The molded body as claimed in either of claims 1 and 2, **characterized in that** it comprises an amount of from 5 to 95% by weight, in particular from 30 to 80% by weight, of plant-derived fiber material, e.g. wood fibers, wood flour, wood chips, cellulose-containing
35 materials, such as waste paper, hemp, straw, flax, agricultural fiber materials, or mixtures thereof.

4. The molded body as claimed in any of claims 1 to

3, **characterized in that** the amount present of the thermoplastic or thermoset or mixture thereof is from 2 to 90% by weight, in particular from 5 to 50% by weight.

5

5. The molded body as claimed in any of claims 1 to 4, **characterized in that** it comprises an amount of from 5 to 50% by weight, in particular from 10 to 30% by weight, of water-binding biopolymer, e.g. starch,
10 starch-containing plant parts, pectin, lignin, hemicellulose, chitin, or mixture thereof.

6. The molded body as claimed in any of claims 1 to 5, **characterized in that** its density is from 0.8 to
15 2.0 g/cm³, preferably from 1.0 to 1.5 g/cm³.

7. The molded body as claimed in any of claims 1 to 6, **characterized in that** it is obtainable via a shaping process that takes place under pressure after a plastic
20 or thermoplastic forming process that takes place under pressure.

8. The molded body as claimed in claim 7, **characterized in that** it can be produced via
25 compression molding, pelletizing, injection-compression molding, or injection molding.

9. A process for production of a molded body as claimed in any of claims 1 to 8, **characterized in that**
30

- raw materials composed of plant- and/or animal-derived fiber material whose moisture content is from 5 to 20% by weight, preferably from 8 to 15% by weight, of at least one thermoplastic or thermoset
35 from the group of polyethylene, polypropylene, PVC, melamine, polyurethane, polyester, polyamide, polymethyl methacrylate, polyvinyl acetate, polystyrene, polycarbonate, polybutene, of at least

one water-binding biopolymer, and, based on the total weight, if appropriate, from 0.2 to 20% by weight of plasticizers, fillers, adhesion promoters, lubricants, heat stabilizers and/or UV stabilizers, antioxidants, or flame retardants, and, if appropriate, water are mixed to give a raw material mixture whose moisture content is > 8% by weight, preferably up to 20% by weight, particularly preferably up to 15% by weight,

- the raw material mixture is, if appropriate, heated,
- the raw material mixture, if appropriate heated, is, if appropriate, formed - plastically or thermoplastically under increased pressure, and also, if appropriate, with increased temperature - to give a molding composition,
- the raw material mixture, if appropriate heated, or the molding composition is shaped under pressure, and also, if appropriate, with increased temperature, to give a non-expanded molded body.

10. The process as claimed in claim 9, **characterized in that** the shaping process that takes place under pressure takes place via compression molding, pelletizing, injection-compression molding, or injection molding.